

## Run of Mine

### Typical chemical analysis and sizes

Grade	Size	Al <sub>2</sub> O <sub>3</sub>	Fe <sub>2</sub> O <sub>3</sub>	Na <sub>2</sub> O	K <sub>2</sub> O
Randalusite	1 – 4 mm 3 – 8 mm	59.5 %	0.70 %	0.10 %	0.20 %
Purusite	0 – 4 mm	58.9 %	0.80 %	0.10 %	0.35 %
Kerphalite KA	0.3 – 1.6 mm	58.7 %	1.05 %	0.10 %	0.35 %
Krugerite K57P	0.5 – 3 mm	57.6 %	0.80 %	0.10 %	0.20 %
Krugerite K55	0.5 – 3 mm	56.6 %	1.10 %	0.15 %	0.45 %
Kerphalite KB	0.3 – 1.6 mm	53.6 %	1.35 %	0.15 %	0.45 %

Technical data sheet for each grade available on request.



154, rue de l'Université  
75007 Paris - France  
Tel. + 33 (0) 1.49.55.65.60  
Fax + 33 (0) 1.49.55.65.55  
E.mail: [sales-andalusite@damrec.com](mailto:sales-andalusite@damrec.com)  
Web site: [www.damrec.com](http://www.damrec.com)