

Sieved and Milled

Typical chemical analysis and sizes

Grade	Size	Al ₂ O ₃	Fe ₂ O ₃	Na ₂ O	K ₂ O
Durandal D59	0 – 1 mm 1 – 3 mm 3 – 5 mm 5 – 8 mm	59.1 %	0.75 %	0.15 %	0.25 %
Kerphalite KA	50 – 350 μ 160 μ 55 μ	59.1 %	0.80 %	0.10 %	0.30 %
Purusite	10 μ 5 μ 2 μ	58.9 %	0.80 %	0.10 %	0.35 %
Durandal D57	0 – 1 mm 1 – 3 mm	57.6 %	0.80 %	0.10 %	0.20 %
Kerphalite KB	160 μ 55 μ	53.6 %	1.35 %	0.15 %	0.45%

Technical data sheet for each grade available on request.



154, rue de l'Université
75007 Paris - France
Tel. + 33 (0) 1.49.55.65.60
Fax + 33 (0) 1.49.55.65.55
E.mail: sales-andalusite@damrec.com
Web site: www.damrec.com